



Colorer votre vie au naturel



TECHNICAL SHEET

TO COLOR YOUR WHITEWASH

Add a SOF-DOSE pot for a bucket of 4 or 8 kg BADI-SOF PLUS.

Always mix the pigment powder in the bucket of BADI-SOF PLUS before adding water.

PACKAGING

Bucket powder 4 or 8 kg

CONSUMPTION

- . Brushed: 100 to 200 g / m²
- . rubbed: 200 to 400 g / m²
- . smoothed: 1 kg / m²

These consumptions are given for information but can vary from one support to another.



-The water mixture should be consumed immediately.

. Outside: do not apply BADI-SOF MORE when temperatures are less than 5 ° C and above 30 ° C, by windy weather, fog density, on frozen or overheated support.



- Swatches of 42 shades

. Opportunity to clarify existing shades

. Samples available

(according to conditions)



Entreprise
du Patrimoine
Vivant



BADISOF PLUS: Limewash

BADISOF PLUS is a mix of lime and mineral additives, reinforced with a silicate, for durability outdoors whose material and Ocre de France's pigments reminiscent authenticity of old walls.

Easy and harmless for use, with BADISOF PLUS your wall can breathe while being impervious to water splashes.

With BADISOF PLUS, you will discover the art of using lime.

BADISOF PLUS exist in white to be colored with Ocre de France's doses of pigment: SOF-DOSE. This limewash have to be applied directly on a mineral and absorbent wall* or on SOFIX (undercoat for whitewash in the case of wall like: old cement plaster, plasterboard, plaster tiles, plaster, painting ... and generally whenever the support is unknown) or SOFADHER.

DILUTION

Pour the contents of the SOF-DOSE in the bucket of BADISOF PLUS, mix well the powder.

-For brush finish aspect

First coat: dilute 1 part of BADISOF PLUS with 2 volumes of water. Stir with an electric mixer (slow speed). Add some water if necessary. Apply evenly making crosses on your wall with a large brush.

Touch dry in 1 hour and can be covered in 6 hours.

Second coat: dilute 1 volume of BADISOF PLUS with 1 volume of water. Adding water if necessary. Mix often during application. Apply evenly making crosses on your first coat.

-For rubbed finished aspect

1 single coat a bit thick: dilute about 1 volume of BADISOF PLUS with 1 volume of water (shaving-cream consistency). Let stand and add water if necessary. Shape as a coating of about 1 mm thick. When your fingers stick no more on the product, rub with a damp sponge (circular motion).

Final drying in 48/72 hours.

-For Smoothed whitewash

Proceed in the same way as the rubbed whitewash.

After having rubbed the whitewash, smooth it with a small spatula stainless steel (fast and short movements).

Touch dry in 24 hours. Recoatable after 48 hours.

For a glossy finish, we advise you to apply the milk wax «Eccocera».

Video of implementation: <https://www.youtube.com/watch?v=AVhR-L960ao>

* Generally, lime enters in a sufficiently thick mineral and absorbent wall, for all thin support (wood, fiber cement...) make prior tests.