



Colorer votre vie au naturel



TECHNICAL SHEET

BADISOF: Limewash

TO COLOR YOUR

WHITEWASH

Add a SOF-DOSE pot for a bucket of 4 or 8 kg BADISOF.

Always mix the pigment powder in the bucket BADISOF before adding water.

PACKAGING

Bucket powder 4 or 8 kg

CONSUMPTION

- . Brush: 100 to 200 g / m²
- . Patina: it depends on the water dilution.



The water mixture should be consumed immediately.



- . Swatch of 42 shades
- . Opportunity to clarify existing shades
- . Samples available (according to conditions)
- . It is possible to apply a wax layer finish to protect from dirt.



Entreprise
du Patrimoine
Vivant



BADISOF is a whitewash of lime, 100% mineral whose material and Ocre de France's pigments reminiscent of old walls. easy and harmless for use, with BADISOF your wall can breathe while being impervious to water splashes.

With BADISOF you will discover the art of the use of lime.

BADISOF exists in natural white ready to be colored with Ocre de France's pigments (SOF-DOSE) or tinted directly in our factory.

This whitewash is applied directly on a mineral and absorbent wall* or on SOFIX (undercoat for whitewash in the case of wall like: old cement plaster, plasterboard, plaster tiles, plaster, painting ...) or on SOFADHER.

DILUTION

Pour the contents of the SOF-DOSE in the bucket of BADISOF, mix well the powder.

for brush finish aspect:

First coat: dilute 1 volume of BADISOF with 2 volumes of water. Stir with an electric mixer (slow speed). Add some water if necessary. Mix often during application. Apply evenly making crosses on your wall with a large brush.

Touch dry in 1 hour and can be covered in 6 hours

Second coat: dilute 1 volume of BADISOF with 1 volume of water. Adding water if necessary. Mix often during application. Apply evenly making crosses on your first coat.

Final drying in 48/72 hours.

For patina or whitewash

The patina is a very liquid coat of a different color or the same color that provides shades.

On your first BADISOF (refer to brush finish aspect), put a diluted coat as follows: 1 volume BADISOF colorful mixed with 10-30 volumes of water.

Apply unevenly to create effects.

Final drying 24-48 hours.

Video of implementation: <https://www.youtube.com/watch?v=DMxfe9LpVIQ>

* Generally, lime enters in a sufficiently thick mineral and absorbent wall, for all thin support (wood, fiber cement ...) make prior tests.